EXPOSURE TIME TABLE FOR KIWO AZOCOL POLY-PLUS RS

EN-08-01

film (image)	Exposure time	
Fine	standard time	-10%
Standard	standard time	
Coarse	standard time	+10%

When repeat size is between two sizes, use the figure of the repeat size below
(e.g. 12 3/8 or 12 2/6 will become 12 inchl)

Repeat size in inch	RM 405	RM 305	RM 215/195 165/125/105	RM 75/32%	RM 75/40%	RM 75/40% TACTILE
	EXPOSURETIME (UNITS)	EXPOSURETIME (UNITS)	EXPOSURETIME (UNITS)	EXPOSURETIME (UNITS)	EXPOSURETIME (UNITS)	EXPOSURETIME (UNITS)
12	385	450	585	945	1015	4500
12 4/8	400	470	610	985	1055	4690
13	415	490	630	1025	1100	4875
13 4/8	430	505	655	1065	1140	5065
14	445	525	680	1105	1180	5250
14 4/8	465	545	705	1145	1225	5440
15	480	565	730	1185	1265	5625
15 4/8	495	580	755	1225	1310	5815
16	510	600	780	1260	1350	6000
16 4/8	525	620	800	1300	1395	6190
17	545	640	825	1340	1435	6375
17 4/8	560	655	850	1380	1480	6565
18	575	675	875	1420	1520	6750
18 4/8	590	695	900	1460	1560	6940
19	605	715	925	1500	1605	7125
19 4/8	625	730	950	1540	1645	7315
20	640	750	970	1580	1690	7500
20 4/8	655	770	995	1615	1730	7690
21	670	790	1020	1655	1775	7875
21 4/8	685	805	1045	1695	1815	8065
22	705	825	1070	1735	1860	8250
22 4/8	720	845	1095	1775	1900	8440
23	735	865	1120	1815	1940	8625
23 4/8	750	880	1140	1855	1985	8815
24	765	900	1165	1895	2025	9000
24 4/8	785	920	1190	1935	2070	9190
25	800	940	1215	1970	2110	9375
25 4/8	815	955	1240	2010	2155	9565
26	830	975	1265	2050	2195	9750
26 4/8	845	995	1290	2090	2240	9940
27	865	1015	1315	2130	2280	10125
27 4/8	880	1030	1335	2170	2320	10315
28	895	1050	1360	2210	2365	10500
28 4/8	910	1070	1385	2250	2405	10690
29	925	1090	1410	2290	2450	10875
29 4/8	940	1105	1435	2325	2490	11065
30	960	1125	1460	2365	2535	11250
30 4/8	975	1145	1485	2405	2575	11440
31	990	1165	1505	2445	2620	11625
31 4/8	1005	1180	1530	2485	2660	11815
32	1020	1200	1555	2525	2700	12000
32 4/8	1040	1220	1580	2565	2745	12190
33	1055	1240	1605	2605	2785	12375
33 4/8	1070	1255	1630	2645	2830	12565
34	1085	1275	1655	2680	2870	12750
34 4/8	1100	1295	1675	2720	2915	12940
35	1120	1315	1700	2760	2955	13125
35 4/8	1135	1330	1725	2800	3000	13315
36	1150	1350	1750	2840	3040	13500